Innovative Service Around the Globe

DATA SHEET

SURFACE-MOUNT CERAMIC MULTILAYER CAPACITORS

C-Array NP0/X7R/Y5V

16 V TO 50 V sizes 0508 (4 x 0402) / 0612 (4 x 0603)

RoHS compliant & Halogen Free



YAGEO Phícomp



SCOPE

This specification describes NP0/X7R/Y5V 4-capacitor Array with lead-free terminations.

YAGEO Phicomp

APPLICATIONS

- Professional electronics
- High density consumer electronics

FEATURES

- Supplied in tape on reel
- Nickel-barrier end termination
- 0508 (4x0402) / 0612 (4x0603) capacitors (of the same capacitance value) per array
- Less than 50% board space of an equivalent discrete component
- High volumetric efficiency
- Increased throughout, by time saved in mounting
- · RoHS compliant
- Halogen Free compliant

ORDERING INFORMATION-GLOBAL PART NUMBER, PHYCOMP CTC & 12NC

All part numbers are identified by the series, size, tolerance, TC material, packing style, voltage, process code, termination and capacitance value. Please note that 12 digits ordering code will expire at the end of 2010.

YAGEO BRAND ordering code GLOBAL PART NUMBER (PREFERRED)

CA <u>xxxx</u> <u>x</u> <u>x</u> <u>xxx</u> <u>x</u> <u>B</u> <u>x</u> <u>xxx</u> (1) (2) (3) (4) (5) (6) (7)

(I) SIZE – INCH BASED (METRIC)

0508 (1220)

0612 (1632)

(2) TOLERANCE

 $J = \pm 5\%$

 $K = \pm 10\%$

 $M = \pm 20\%$

Z = -20% to +80%

(3) PACKING STYLE

R = Paper/PE taping reel; Reel 7 inch

P = Paper/PE taping reel; Reel 13 inch

(4) TC MATERIAL

NPO

X5R

X7R

Y5V

(5) RATED VOLTAGE

7 = 16 V

8 = 25 V

9 = 50 V

0 = 100 V

(6) PROCESS

N = NP0

B = class 2 material

(7) CAPACITANCE VALUE

2 significant digits+number of zeros

The 3rd digit signifies the multiplying factor, and letter R is decimal point

Example: $121 = 12 \times 10^{1} = 120 \text{ pF}$


CONSTRUCTION

YAGEO Phicomp

The capacitor consists of a rectangular block of ceramic dielectric in which a number of interleaved metal electrodes are contained. This structure gives rise to a high capacitance per unit volume.

The inner electrodes are connected to the two end terminations and finally covered with a layer of plated tin (NiSn).


The terminations are lead-free. An outline of the structure is shown in Fig.I.



DIMENSIONS

Table I		
TYPE	0508 (4 X 0402)	0612 (4 X 0603)
L (mm)	2.0 ±0.15	3.2 ±0.15
W (mm)	1.25 ±0.15	1.60 ±0.15
$T_{min.}$ (mm)	0.50	0.70
$T_{max.}$ (mm)	0.70	0.90
A (mm)	0.28 ±0.10	0.4 ±0.10
B (mm)	0.2 ±0.10	0.3 ±0.20
P (mm)	0.5 ±0.10	0.8 ±0.10

OUTLINES





NP0/X7R/Y5V

16 V to 50 V

CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 2 Temperature characteristic material from NP0

CAPACITANCE	0508 (4 × 0402)	0612 (4 × 0603)		
	50 V	100V	50 V	100V
10 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
15 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
18 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
22 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
33 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
39 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
47 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
56 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
68 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
82 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
100 pF	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1
120 pF	0.6±0.1		0.8±0.1	0.8±0.1
150 pF	0.6±0.1		0.8±0.1	0.8±0.1
180 pF	0.6±0.1		0.8±0.1	0.8±0.1
220 pF	0.6±0.1		0.8±0.1	0.8±0.1
270 pF			0.8±0.1	0.8±0.1
330 pF			0.8±0.1	0.8±0.1
390 pF			0.8±0.1	0.8±0.1
470 pF			0.8±0.1	0.8±0.1
560 pF				
680 pF				
820 pF				
I.O nF				

NOTE

Values in shaded cells indicate thickness class in mm



16 V to 50 V

CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 3 Temperature characteristic material from X7R

YAGEO Phicomp

CAPACITANCE		suc material nom		0612 (4 × 0603)			
	16 V	25 V	50 V	16 V	25 V	50 V	100V
1.0 nF	0.6±0.1	0.6±0.1	0.6±0.1	0.8±0.1	0.8±0.1	0.8±0.1	
1,2 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
1.5 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
1.8 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
2.2 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
2.7 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
3.3 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
3.9 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
4.7 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
5.6 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
6.8 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
8.2 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	
10 nF	0.6±0.1	0.6±0.1		0.8±0.1	0.8±0.1	0.8±0.1	0.85±0.1
12 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	0.85±0.1
15 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	0.85±0.1
18 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	0.85±0.1
22 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	0.85±0.1
27 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	
33 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	
47 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	
56 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	
68 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	
82 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	
100 nF	0.6±0.1			0.8±0.1	0.8±0.1	0.8±0.1	
220 nF				0.8±0.1			
470 nF				0.8±0.1			

Values in shaded cells indicate thickness class in mm



Surface-Mount Ceramic Multilayer Capacitors 4C-Arroy

NP0/X7R/Y5V

16 V to 50 V

CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 4 Temperature characteristic material from Y5V

 $0612 (4 \times 0603)$ **CAPACITANCE**

25 V

10 nF	
22 nF	
47 nF	£6.0
100 nF	

NOTE

Values in shaded cells indicate thickness class in mm

THICKNESS CLASSES AND PACKING QUANTITY

Table 5				
SIZE	THICKNESS	TAPE WIDTH QUANTITY	Ø180 MM / 7 INCH	Ø180 MM / 13 INCH
CODE	CLASSIFICATION	PER REEL	Paper	Paper
0508	0.6 ±0.1 mm	8 mm	4,000	20,000
0612	0.8 ±0.1 mm	8 mm	4,000	15,000



NP0/X7R/Y5V

16 V to 50 V

ELECTRICAL CHARACTERISTICS

4C-ARRAY DIELECTRIC CAPACITORS; NISN TERMINATIONS

Unless otherwise stated all electrical values apply at an ambient temperature of 20±1 °C, an atmospheric pressure of 86 to 106 kPa, and a relative humidity of 63 to 67%.

Table 6		
DESCRIPTION		VALUE
Capacitance range		10 pF to 100 nF
Rated voltage		
	NP0	50 V
	X7R	16 V to 50 V
	Y5V	0612: 25 V
Capacitance tolerance		
	NP0	±5%, ±10%
	X7R	±10%, ±20%
	Y5V	-20% to +80%
Dissipation factor (D.F.)		
	NP0	≤ 0.1%
	X7R	16 V ≤ 3.5%, 25V ≤ 2.5%, 50V ≤ 2.5%
		0508/12nF~100nF/16V, Df≤5%
	Y5V	0508 ≤ 9%, 0612 ≤ 7%
Insulation resistance after I minute at U_r (DC)		$R_{\rm ins} \ge 10~{\rm G}\Omega$ or $R_{\rm ins} \times C_r \ge 500$ seconds whichever is less
Maximum capacitance change as a function of temperature (temperature characteristic/coefficient):	ıre	
	NP0	±30 ppm/°C
	X7R	±15%
	Y5V	+22% to -82%
Operating temperature range:		
	NP0	-55 °C to +125 °C
	X7R	_55 °C to +125 °C
	Y5V	-30 °C to +85 °C

